



BEFORE



DuraPrep[®] Prep 400
APPLICATION



AFTER

AN AFFORDABLE SOLUTION FOR COMBATING GRAFFITI

Graffiti-Resistant Coating System

Graffiti costs U.S. building owners an estimated \$25 billion per year.

Steelscape offers a factory applied graffiti-resistant coating system specifically formulated to work with PPG Industries' DuraPrep[®] Prep 400 graffiti remover.

This innovative coating system includes a primer, a color coat, and a graffiti-resistant clear coat. The clear coating works as a barrier of protection over the color coat layer and prevents most graffiti material from gripping or shadowing the surface. The DuraPrep Prep 400 is applied directly on the graffiti and easily wipes it off of the pre-painted graffiti-resistant coated metal surface.

The graffiti removal system offers building owners an easy and fully tested maintenance method to safely remove graffiti... keeping buildings looking their best.



The Graffiti Removal System Includes:

Graffiti-Resistant Clear Coating System in four gloss options.

- #17394 Low Gloss Graffiti-Resistant Coating (10 - 15)
- #17395 Medium Gloss Graffiti-Resistant Coating (25 - 35)
- #17396 Medium Gloss Graffiti-Resistant Coating (50 - 70)
- #17392 High Gloss Graffiti-Resistant Coating (80+)

Graffiti Remover DuraPrep[®] Prep 400 available through PPG Industries Inc.

DuraPrep[®] Prep 400 is a water based, non-flammable spray that is environmentally friendly with no caustic chemicals.

To order DuraPrep[®] Prep 400 at a location near you, go to www.ppgpaints.com/products/duraprep-prep400-overspray-remover



Let Steelscape help protect your investment.

TEST	SPECIFICATION	RESULTS
Dry Film Thickness (nominal)	ASTM D5796	Standard Primer .15-.30mil Standard Topcoat .70-.80mil GR Clear .45-.55mil
Gloss 60° specular gloss	ASTM D523	Low Gloss Graffiti-Resistant Coating (10 - 15) Medium Gloss Graffiti-Resistant Coating (25 - 35) Medium Gloss Graffiti-Resistant Coating (50 - 70) High Gloss Graffiti-Resistant Coating (80+)
Flexibility, T-bend	ASTM D4145	0T – 1T; No pick-off
Chemical Resistance	ASTM D1308	10% Muriatic Acid, 15 minutes: No discoloration 25% NaOH, 1 hour: No effects
Humidity	ASTM D2247 ASTM D714	Passes 1,000 hours No #8 blisters. 100% relative humidity @ 95°F
South Florida Exposure	ASTM D2244	Maximum 5 NSB units color change, <0.01 mils/year film erosion

LIMITED 40 YEAR WARRANTY, please contact your Steelscape representative for a complete sample warranty.



PPG Industries Graffiti-Resistant Clear Coating System meets or exceeds the American Architectural Manufacturers Association (AAMA) 2605 standards for performance and longevity.

DURAPREP® is a registered trademark of PPG Architectural Finishes, Inc.