



AGELESS BEAUTY. UNCOMPROMISED STRENGTH.

Eternal Collection®

The Eternal Collection encompasses four elegant, inspiring colors exclusive to Steelscape. Providing the same engaging luster as Steelscape's Vintage®, the Eternal Collection expands the breadth of color options available to the design community.

The unique combination of pigmentation and gloss provides a rich, warm color and distinctive surface sheen. Designed to complement the dynamic qualities of the built environment, the Eternal Collection is the perfect finish for roofing and siding applications. Backed by the corrosion-resistance of ZINCALUME® and supported by a robust 20-year finish warranty, the Eternal Collection is the durable, yet distinctive finish for your next inspiring building design.



Ironstone
SRI 29 • 21583



Rainforest
SRI 25 • 21584



Sungold
SRI 36 • 22070



Urban Slate
SRI 24 • 21585

Representation of color may vary due to printing limitations. Actual metal samples are available upon request.

Due to the unique nature of this product, color may vary slightly from batch to batch. Batches should not be mixed on projects.

PERFORMANCE QUALITIES

Substrate: AZ50 ZINCALUME® Coated Steel
(ASTM A792/A792M)

Thickness: .0236 (24ga) or .0296 (22ga)

Steel Grade: 80 or 50

Finish: Durable finish with a proprietary distinctive metallic luster using fluorocarbon pre-paint technology

Surface Appearance: Smooth and free of blistering and other surface imperfections

Film Thickness: Top System Finish: 0.55 – 0.65 mil
(ASTM D5796)

Bottom System Finish:
Primer = 0.15 – 0.25 mil
Backer = 0.30 – 0.40 mil

Specular Gloss: 60 Degree Specular Gloss =
(ASTM D523) 5% - 20%; Sungold is 10% - 20%

Hardness: HB Min
(ASTM D3363)

Cure Test: 50 Double MEK Rubs Minimum
(ASTM D5402)

Cross Hatch Adhesion: No Tape Off
(ASTM D3359)

Reverse Impact: No Tape Off, 80 inch-pounds of force
(ASTM D2794)

T-Bend Flexibility: 2T No Tape Off
(ASTM D4145)

Humidity Resistance: 1,000 Hours – Passes
(ASTM D2247) (100% RH @ 100 degrees F)

Salt Spray Resistance: 1,000 Hours – Passes
(ASTM B117) (5% Salt Spray @ 95 degrees F)

Production Location: Rancho Cucamonga, CA